



AL812 – 100/125kg Fast Recovery PVC Foam

PROPERTY	AVERAGE VALUE
Density	100 – 125 kg/m ³
Compression Set	<20 %
Shore Hardness OO Scale	7-30
Elongation at Break	> 120 %
Temperature Range (Constant)	- 30 °C / + 60 °C
Temperature Range (Intermittent)	+ 70 °C
Tear Strength	>0.7 N/mm
Waterseal Compression	> 90 %
Flame Resistance (> 6mm)	FMVSS302 - Pass
Environmental Protection	CFC & HCFC Free

The above figures are average values and should be considered as guidelines not specifications. While reasonable care has been taken to ensure that this data is representative, Alanto Ltd does not warrant or otherwise guarantee, expressly or impliedly, the suitability, accuracy, reliability or completeness of the information.

We recommend evaluation prior to use to ascertain the suitability of the material for the application.

Unit 21 & 23 Regal Drive, Walsall Ent Park, Walsall, WS2 9HQ
Tel : 01922 723740 – Fax : 01922 724284 – Email : sales [@alanto.co.uk](mailto:sales@alanto.co.uk)



AL820 – 210 kg/m³ Fast Recovery PVC Foam

PROPERTY	SPECIFICATION	AVERAGE VALUE	UNIT
Density		200 - 220	Kg / m ³
Tensile Strength	DIN 53571	> 279	kPa
Elongation at Break	DIN 53571	> 125	%
Compression Set (50%/23°C/72Hrs)	DIN 53572	< 30	%
Compression Deflection (0s)	ASTM 1667	25 - 50	kPa
Compression Deflection (60s)	ASTM 1667	10 – 35	kPa
Shore Hardness		25 - 42	
Water Absorption		< 11	%
Compression Water Seal (U-Test)		> 20	%
Flammability	FMVSS302	<100mm >4mm	mm / min
Temperature Range		- 30 / +80	°C

The above figures are average values and should be considered as guidelines not specifications. While reasonable care has been taken to ensure that this data is representative, Alanto Ltd does not warrant or otherwise guarantee, expressly or impliedly, the suitability, accuracy, reliability or completeness of the information.

We recommend evaluation prior to use to ascertain the suitability of the material for the application.

Unit 21 & 23 Regal Drive, Walsall Ent Park, Walsall, WS2 9HQ
Tel : 01922 723740 – Fax : 01922 724284 – Email : sales@[alanto.co.uk](mailto:sales@alanto.co.uk)