



## **SPECIFICATION SHEET**

### **AL55 SOLID**

| <b>Desc.</b>                                | <b>Value</b>    | <b>Unit</b> |
|---|-----------------|-------------|
| Shore Hardness                              | <b>55 +/- 5</b> | <b>OO</b>   |
| Tensile Strength                            | 9               | MPa         |
| Tear Strength                               | 13              | N/mm        |
| Elongation                                  | >300            | %           |
| Temperature Range                           | -60 / +230      | °C          |
| Compression Set (BS 903 Pt A6)              | 20              | %           |
| Flame Resistance (CAA 8 Iss 2 / FAR 25.853) | PASS            |             |
| Environmental Protection                    | CFC Free        |             |

*The above figures are average values and should be considered as guidelines not specifications. While reasonable care has been taken to ensure that this data is representative, Alanto Ltd does not warrant or otherwise guarantee, expressly or impliedly, the suitability, accuracy, reliability or completeness of the information.*

*We recommend evaluation prior to use to ascertain the suitability of the material for the application.*

Unit 21 & 23 Regal Drive, Walsall Ent Park, Walsall, WS2 9HQ  
Tel : 01922 723740 – Fax : 01922 724284 – Email : sales [@alanto.co.uk](mailto:sales@alanto.co.uk)