



SPECIFICATION SHEET

AL500 Commercial Economy Solid

Characteristic	Typical Value	Unit
Elastomer	Natural	
Colour	Black	
Hardness	65° +/- 5°	Shore A
S.G	1.5	g/cm ³
Tear	9.5	Kn/m
Tensile	2.5 min	MPa
Elongation	200 min	%
Compression Set (100°C/22hrs)	90	%
Operating Temperature	-20 to +70	°C

The above figures are average values and should be considered as guidelines not specifications. While reasonable care has been taken to ensure that this data is representative, Alanto Ltd does not warrant or otherwise guarantee, expressly or impliedly, the suitability, accuracy, reliability or completeness of the information.

We recommend evaluation prior to use to ascertain the suitability of the material for the application.

Unit 21 & 23 Regal Drive, Walsall Ent Park, Walsall, WS2 9HQ
Tel : 01922 723740 – Fax : 01922 724284 – Email : sales [@alanto.co.uk](mailto:sales@alanto.co.uk)