



SPECIFICATION SHEET

FIRESEAL

SPECIFICATION	TEST METHOD	RESULT
Density	BS EN ISO 845	> 90 kg/m ³
Colour		Dark Grey
Thickness		6mm – 100mm
Fire Propagation Index	BS 476 part 6	< 12 >6mm
Surface Spread of Flame	BS 476 part 7	Class 1
Building Regulations Paragraph A13 (b)	BS 476 part 6 & 7	Class 0
Fire Performance	EN13501-1 Euro Class	B-sl,d0
Operating Temperature		-30 to +100 °C
UL94 Classification	UL94	94 V-0
Surface Burning Behaviour	ASTM E84-09	Flame Spread index 10 Smoke Developed index 20
Air Erosion Resistance	ASTM C1071-05 12.7 6-50mm	Pass
Fungus Resistance Test	ASTM G21-96	Does not support growth
Mildew (Fungus) Resistance	ASTM D-2020-92	Does not support growth
Water Vapour Sorption	ASTM C1104-06	< 9 %
Thermal Conductivity	ASTM C518-04	0.32 Btu-in/ft ² -hr°F@6mm
Corrosiveness (galvanized steel)	ASTM C665-95	Pass
Hot Surface Performance @ 100 °C 96hr	ASTM C411-04	Pass

Acoustic Performance Information

Sound Absorption @ 12mm	NRC-0.30
Sound Absorption @ 25mm	NRC-0.45
Sound Absorption @ 50mm	NRC-0.75

Certification of Euroclass 6mm-50mm adhered, 50mm unadhered

The above figures are average values and should be considered as guidelines not specifications. While reasonable care has been taken to ensure that this data is representative, Alanto Ltd does not warrant or otherwise guarantee, expressly or impliedly, the suitability, accuracy, reliability or completeness of the information.

We recommend evaluation prior to use to ascertain the suitability of the material for the application.

Unit 21 & 23 Regal Drive, Walsall Ent Park, Walsall, WS2 9HQ
Tel : 01922 723740 – Fax : 01922 724284 – Email : sales [@alanto.co.uk](mailto:sales@alanto.co.uk)